

Rubber Accelerators

TBBS

Product Information

N-tert-Butyl-2-benzothiazolesulfenamide
Powder Form
As primary accelerator

Specification	Unit	Typical Value
Appearance	-	Pale yellow/pink powder
Assay	%	95.0 min
Initial melting point	°C	104 min
Loss on drying	%	0.40 max
Ash content	%	0.40 max
Residues on 150µm sieve	%	0.1 max
Typical Density	g/cm ³	1.280

Description:

Pale yellow or pink fine powder, also available in granular form and in oil-coated powder form.

Packaging:

Paper bags (Net 25 kg each), palletised.

Application:

It is used as primary accelerator. It offers fast curing, and gives good modulus development.

Caution for Storage:

Store dry on pallets at cool and well-ventilated area, maximum 90% R.H., not exposed to heating or UV light. Avoid contact with water, acids and alkalis.

For more information:

Please contact our local distributor.

Technical information regarding the composition, properties or use of the product described in this Product Information is believed to be reliable. However, no representation or warranty is made with respect thereto except as made by Huan Ya Chemical Company in writing at the time of sale.

Rev01/0012

新加坡环亚化工私人有限公司
PLANET ASIA PTE LTD
20 AYER RAJAH CRES #09-15
SINGAPORE 139964

E-mail: enquiry@planasia.com
Tel # +65 6872 2522
Fax # + 65 6872 5655
<http://www.planasia.com>